

MasterEmaco S 5400CI

High-strength, shrinkage compensated, fibre reinforced, structural repair mortar with active corrosion inhibition

Material Description

MasterEmaco S 5400CI is a single component, extra high-strength, high modulus, shrinkage compensated structural repair mortar that meets the requirements of EN 1504 part 3 class R4. **MasterEmaco S 5400CI** contains Portland cement, graded sands, selected polymer fibres and special additives to significantly reduce the risk and incidence of shrinkage cracking. When mixed with water, it forms a highly thixotropic mortar that can easily be spray or trowel applied.

Areas of Application

MasterEmaco S 5400CI is used for the structural repair of concrete elements such as:

- Columns, piers and cross beams of all bridges
- Cooling towers and chimneys and other industrial environments
- Marine structures, water treatment and sewerage facilities
- Tunnels, pipes, outfalls and all below ground construction especially in harsh ground conditions

Characteristics and Benefits

- Versatile – can be applied in extreme environments where active corrosion inhibition is required
- Shrinkage compensation systems and fibre reinforcement – minimise crack tendency
- Highly thixotropic – can be applied up to 50 mm without the need of secondary reinforcement
- High early and ultimate strengths – matches high strength concrete found in structures
- Outstanding workability – easy placing and finishing for applicators
- High modulus and excellent adhesion – ensuring load transfer in structural repair
- Excellent freeze/thaw resistance – suitable for all climates
- High carbonation resistance – suitable for exposed repairs in urban environments
- Sulphate resistant – suitable for contact with ground waters
- Very low permeability to water and chlorides – protection of reinforcing steel

- Low chromate (Cr[VI] < 2 ppm) – low risk of skin irritation
- Chloride-free – does not add to the chloride load in contaminated structures
- Approved to AS/NZS 4020:2018 (tested to the maximum exposure level) - suitable for contact with potable water.

Properties

| | |
|--|-------------------------------|
| Appearance | Grey powder |
| Layer thickness | Min. 5mm Max. 50mm |
| Density | Approx. 2.2 g/cm ³ |
| Mixing water per 20kg bag | Approx. 3.0 – 3.4 litres |
| Working time | 45 – 60 minutes |
| Application Temperature (support and material) | Between +5 and +35°C |

| | |
|---|---|
| Compressive strength - after 1 day - after 7 days - after 28 days AS 1478.2 Appendix A (Restrained) | ≥ 16 MPa ≥ 45 MPa ≥ 70 MPa |
| E-Modulus (28 days) EN 13412 | ≥ 26 GPa |
| Cracking tendency (I) Coutinho type ring | No cracking after 180 days |
| Resistivity | 216000 Ω.cm |
| Permeability risk for Chlorides and sulphates FM5-578 | Very low |
| AS/NZS 4020:2018 | Suitable for contact with potable water |
| VOC Content SCAQMD Test method 304-91 | 8g/L |

Application

Surface Preparation

Concrete must be fully cured with a minimum direct tensile strength of 1.5 MPa. All loose traces of concrete or mortar, dust, grease oil, etc. must be removed. Damaged or contaminated concrete shall be removed to obtain a keyed aggregate exposed surface. Non-impact/ vibrating cleaning methods, e.g. grit or high pressure water blasting are recommended to obtain a CSP 5 or greater profile.

MasterEmaco S 5400CI

High-strength, shrinkage compensated, fibre reinforced, structural repair mortar with active corrosion inhibition

Cut the edges of the repair vertically to a minimum depth of 5 mm. Clean all exposed reinforcement to a minimum grade of Sa 2 according to ISO 8501-1 / ISO 12944-4. Ensure back of rebar is also clean. In case of chloride contamination of the concrete, or when depth of cover is less than 5mm the reinforcement should be protected by using **MasterEmaco P 5000AP**.

Mixing

Only full bags are mixed. Damaged or opened bags should not be used. Mix **MasterEmaco S 5400CI** in a forced action pan mixer, or with a helical paddle attached to a low speed (300-600rpm) mixer for 3 minutes until a lump free, plastic consistency is achieved. Only use clean water. Mixing water needed: 3.0 to 3.4 litres per 20kg bag depending upon consistency required. Allow the mortar to rest for 2 - 3 minutes and then remix briefly, adjusting the consistency when required, without exceeding the maximum water demand.

Priming Concrete

No special primer is required. To obtain extra strong bonding, the damp substrate can be primed with a slurry brush coat of **MasterEmaco S 5400CI** (2 parts powder to 1 part water) or **MasterEmaco P 157**. Alternatively, **MasterEmaco P 5000AP** can also be applied as the bonding slurry.

Mortar Application

The minimum temperatures must be maintained during application and for at least 24 hours thereafter for optimum curing of the product. The prepared substrate should be pre-soaked, preferably for 24 hours, but at least 2 hours before applying **MasterEmaco S 5400CI**. The surface must be saturated surface dry, but without standing water. **MasterEmaco S 5400CI** can be spray, trowel or hand applied. Apply mixed product directly to the prepared damp substrate, or wet in wet onto the primed surface. Spraying the material with the necessary pressure will ensure good adhesion of the material. A thin scratch coat or contact layer before building up to the required thickness, wet on wet, will improve adhesion especially in case of hand application. Apply to the desired layer thickness of 5mm to max 50 mm and level using a screeding bar, trowel or wooden board.

Can be applied in thicker layers in smaller patches or where additional reinforcement is present. Smoothing with a trowel or finishing by float or sponge can be done as soon as the mortar has begun to stiffen.

Curing

Following curing methods are advisable - polyethylene film, damp cloths, MasterKure curing agents.

Estimating Data

One 20kg bag will yield approximately 10.5 litres of mortar. Approx. 2.2 kg of mixed product per m² per mm layer thickness (approx. 2 kg of dry powder per m² and mm layer thickness).

| MasterEmaco S 5400CI | | | | |
|----------------------|---------------------------------|----------------|----------------------|------------------------------|
| L | Thickness in mm /m ² | m ³ | bags /m ³ | m ² /mm thickness |
| 10.5 | 10.5mm | (0.0105) | 95 | 10.5 m ² |

This consumption is theoretical and depends on the roughness of the support amount of rebar, wastage etc. It should be verified in each particular job by means of "in situ" tests.

Packaging

MasterEmaco S 5400CI is available in 20kg bags.

Storage & Shelf Life

Store in cool and dry warehouse conditions. Shelf life in these conditions is 12 months in unopened original bags.

Precautions

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Safety Data Sheet (SDS) from our office or website.

MasterEmaco S 5400CI

High-strength, shrinkage compensated, fibre reinforced, structural repair mortar with active corrosion inhibition

Disclaimer

MasterEmaco-S5400CI-ANZ-VI4-0523

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.

MB Solutions Australia Pty Ltd

ABN 69 634 934 419
 Unit 102, 2 Burbank Place
 Norwest NSW 2153

Freecall: 1300 227 300

www.master-builders-solutions.com/en-au

MB Solutions New Zealand Ltd

45C William Pickering Drive
 Albany, Auckland
 New Zealand

Phone: +64 9 414 7233

Emergency Advice:

1300 954 583 within Australia (24hr)
 0800 001 607 within New Zealand

