

MasterEmaco S 820CI

Cementitious spray applied repair mortar with active corrosion inhibition

Material Description

MasterEmaco S 820CI is a ready-to-use, cement based shotcrete mix with reduced rebound and active corrosion inhibition. It is specially designed for civil and mining applications using either the wet or dry shotcreting systems.

Areas of Application

- Repairs to the underside of bridge decks, bridge piers and beams, tunnels, drains, sea walls, and culverts.
- Reinstating eroded concrete in sewers prior to the application of MasterEmaco S 680.
- Tunnel linings and embankment stabilisation.

Characteristics and Benefits

- Active corrosion inhibition - reduced possibility of incipient anodes and longer lasting patches
- Easy to use - requires only the addition of potable water for mixing or spraying
- Versatile - is easily sprayed using the wet mix shotcrete system or dry mix systems
- Good working time - over one hour at 21°C
- Addition of polymer - improved bonding and impermeability of hardened shotcrete
- Controlled shrinkage - reduced cracking tendency

Properties

Age	Compressive Strength MPa	Flexural Strength MPa
1 day	30.0	3.0
3 days	45.0	4.0
7 days	60.0	5.0
28 days	70.0	6.0

All performance data is determined by testing actual, in-place shotcreted specimens such as cores and beams taken from test panels.

Reasonable variations from the data shown can be expected, depending on the care taken in evaluating test specimens, and jobsite conditions such as the quality of substrate preparation,

level of expertise of the nozzleman, curing procedures and weather.

Application

Prepare the surface to be shotcreted by removing all unsound concrete, dirt, dust and debris. A surface profile of CSP 7 or greater is desired. For structural repairs to existing concrete members, saturate the properly prepared concrete surface for a minimum of 7 hours prior to shotcreting.

Mix MasterEmaco S 820CI with approximately 1.8-2.5 litres of water per 20kg bag.

MasterEmaco S 820CI can be shotcreted in depths ranging from 10 - 150mm in one pass.

Curing

Proper curing is extremely important. Wet curing is recommended for the first 3-5 days, after that time continue curing by the use of a quality curing compound such as MasterKure 404 or MasterKure 250. If MasterEmaco P 157 is mixed with MasterEmaco S 820CI then only MasterKure 404 should be used. Do not use solvent-based curing compounds such as MasterKure 402.

Estimating Data

One 20kg bag of MasterEmaco S 820CI mixed with water yields approximately 10.2 litres (0.0102m³).

MasterEmaco S 820CI				
L	Thickness in mm /m ²	m ³	bags /m ³	m ² /mm thickness
10.2	10.2mm	(0.0102)	98	10.2 m ²

Allowance must be made for rebound and cut off for finishing which will reduce the coverage accordingly.

An allowance of 5-10% can be made for rebound which assumes an experienced nozzleman and ideal conditions. For overhead spraying the rebound allowance may be increased to 10-50%.

MasterEmaco S 820CI

Cementitious spray applied repair mortar with active corrosion inhibition

Packaging

MasterEmaco S 820CI is available in 20kg bags.

Storage & Shelf Life

MasterEmaco S 820CI has a shelf life of 12 months. Store out of direct sunlight, clear of the ground on pallets protected from rainfall.

Precautions

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Safety Data Sheet (SDS) from our office or website.

Disclaimer

MasterEmaco-S820CI-ANZ-VI I -0523

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.

MB Solutions Australia Pty Ltd

ABN 69 634 934 419
 Unit 102, 2 Burbank Place
 Norwest NSW 2153

Freecall: 1300 227 300

www.master-builders-solutions.com/en-au

MB Solutions New Zealand Ltd

45C William Pickering Drive
 Albany, Auckland
 New Zealand

Phone: +64 9 414 7233

Emergency Advice:

1300 954 583 within Australia (24hr)
 0800 001 607 within New Zealand

