

## MEGAPOXY HT

### NON - SAG HYDROPHILIC EPOXY

Megapoxy HT is suitable for application on overhead, vertical or inclined surfaces. Because of its hydrophilic nature it can be used under damp conditions.

Megapoxy HT is designed for application by spraying equipment and can be applied in thick films on vertical and overhead surfaces. Megapoxy HT is also suitable for applications by brushing, knifing, trowelling and other techniques of placement of epoxy resins, with the exception of casting. The non-sag characteristic assists greatly in underwater applications.

Mixing proportions	: 3 parts "A" to 1 part "B" by volume
Colour when mixed	: Translucent green
Work time ( 1 litre mix )	: 30 minutes at 25°C
Minimum cure time	: 24 hours at 25°C

### CURED PROPERTIES

Compressive strength	: 110 MPa
Compressive modulus	: 3.4 GPa
Tensile strength	: 61 MPa
Bond strength, new to Old concrete	: Passes University of Arizona test

### MEGAPOXY HT ( 1 volume ) - SILICA 50N SAND ( 2 volumes )

Compressive strength	: 80 MPa
Compressive modulus	: 9.8 GPa
Tensile strength	: 52 MPa
Adhesive bond strength	: 12 MPa

### AVAILABILITY

Megapoxy HT is available in 4 litre and 20 litre kits. In each kit Part "A" and Part "B" are premetered in correct mixing ratio for immediate use.

